



The Factory Line

Cool, individual, timeless –
minimal industrial style
through exposed concrete look

LOBA FactoryBase and the finish 2K FactoryStyle combine into a waterbased system. It preserves the natural coloring and appearance of decorative levelling compounds and provides a wide range of design options creating a timeless industrial look. The low-emission system set-up transforms cement-based levelling compounds into slip-resistant floors with high mechanical resistance.



Why end users are convinced of LOBA Factory Line:

- Durable look – high resistance to mechanical wear
- Uniform matte surface
- Particularly low emission
- Increased anti-slip properties
- Easy and convenient cleaning

Why contractors are convinced of LOBA Factory Line:

- Excellent application performance – safe and easy to use
- Time efficient, thanks to a 2-coat system (1 x FactoryBase, 1 x 2K FactoryStyle)
- Can be used on numerous cement-based levelling compounds
- Particularly low emission, EMICODE® EC1 Plus
- Low VOC, GISCODE W2+ or W2/DD+
- Certified anti-slip properties according DIN 51130, evaluation group R9

Special features

The LOBA FactoryBase and 2K FactoryStyle system has been specially developed for the finishing of exposed concrete surfaces. The primer ensures reliable adhesion of the finish to the levelling compound. The extra-matte finish preserves the natural color of the levelling compound and is extremely abrasion-resistant.

Range of use

Suitable for finishing levelling compounds that are approved for use as wear surface. For heavily stressed flooring in residential areas and commercial applications.



Here you will find a list of LOBA approved levelling compounds



FactoryBase

Article No. 11751

Available in 5L

GISCODE W2+



Application

Subfloor preparation

- Apply LOBA approved levelling compounds according to the manufacturer's instructions
- Prepare the subfloor properly
- Do not sand the filling compound, any unevenness should be partially removed with a sharp, knife blade



2K FactoryStyle

Stress level



Article No. 11743

Available in extramatt (5 kg)

GISCODE W2/DD+



R9
6-10⁺

Primer

- Apply 1x FactoryBase
- Application device: roller Microfibre 100-120
- Material consumption: 100 ml(g)/m² = 10 m²/l(kg)
- Dry time: minimum 3 hours, only start working again when the surface has a uniform dried-through, cured appearance, maximum 24 hours

Finish

- 2K FactoryStyle: Shake, add the hardener in a ratio of 10:1 and mix in by shaking
- Apply 1x 2K FactoryStyle
- Application device: roller Microfibre 100-120
- Material consumption: 100 ml(g)/m² = 10 m²/l(kg)

Please observe the detailed technical information, processing instructions and assembly recommendations.

Do you have any questions? Please do not hesitate and contact us:



More Information
FactoryBase



More Information
2K FactoryStyle

LOBA GmbH & Co. KG

Leonberger Str. 56-62 | 71254 Ditzingen | Germany | Fon: +49 7156 357-0 | Fax: +49 7156 357-211 | e-mail: service@loba.de | www.loba.de